

FORMS OF SUPPLY

LAUROKYD® F-396: 60% in xylene

LAUROKYD F-396**TYPE AND USE**

LAUROKYD F-396 is a short oil alkyd resin suitable for very fast air drying industrial coatings.

LAUROKYD F-396 is also suitable for radiator paints by dipping application.

PRINCIPAL PROPERTIES

Good yellowing resistance on exposure to heat and light.

Very good hardness, gloss and gloss retention.

Very good adhesion on metal substrates.

COMPOSITION

Type of oil: Selection of oils and fatty acids

Oil length: approx. 40%

Phthalic anhydride: approx. 30%

Type of polyol: Pentaerythritol, TMP

SOLUBILITY

White spirit: limited

Aromatic hydrocarbons: complete

Esters, ketones: complete

Alcohols: insoluble

TECHNICAL CHARACTERISTICS

Non-volatile content (ELOT EN ISO 3251) 60% ± 2%

Viscosity, 60% in xylene

25°C (ELOT EN ISO 2884) mPa.s 5000 – 8000

Acid value (ELOT EN ISO 3682 on n.v.) max. 12

Colour, 50% nv

Gardner colour scale (ELOT EN ISO 4630) max. 6

OTHER CHARACTERISTICS (informative)

Flash point approx. 25°C

The information contained herein is provided in good faith and is to the best of our knowledge accurate. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety and additional information please refer to the Material Safety Data Sheet as well as to other informative documents accompanying the product.

LAUROKYD F-396 en
Version 1.0